

Influence of cracks on the carbonation resistance of concrete structures

A.AL-Ameeri

University of Brighton, UK and University of Babylon, Iraq

M. I. Rafiq and O.Tsioulou

University of Brighton, UK





ABSTRACT

Carbonation-induced corrosion of steel rebar embedded in concrete is one of the major issues influencing the durability of reinforced concrete structures. It has been acknowledged that structural cracks in concrete influences the carbon dioxide (CO₂) diffusivity and accelerates the carbonation-induced reinforcement corrosion, however most of the previous studies on the carbonation induced corrosion have concentrated on the un-cracked / unloaded concrete. This study investigates the impact of cracks caused by loading on the depth of carbonation into concrete. Concrete prisms (100x100x500 mm) were subjected to four different crack widths (0, 0.05-0.15 mm, 0.15-0.25 mm and 0.25-0.35 mm) and the carbonation depth was determined using an accelerated environment test programme based on the CEN/TS 12390-10:2007 and XRD analysis. The impact of replacing OPC cement by pulverized fuel ash (PFA) and ground granulated blast furnace slag (GGBS) on the carbonation depth in cracked concrete was also investigated. The results show a considerable influence of crack width on the depth of carbonation and the X-ray powder diffraction analysis (XRD) confirms these results. The penetration of carbon dioxide and accumulation of carbonation compound (CaCO₃) were found to be concentrated at crack locations, whereas the carbonation depths at other locations were found to be less than the carbonation depth in un-cracked concrete. The results also demonstrate a significant increase in the penetration of carbonation due to the addition of supplementary materials in the samples when compared to the reference mixes.

Keywords: Carbonation, Deterioration, Phenolphthalein Indicator, XRD analysis and Cracked concrete.

1.0 INTRODUCTION

Carbonation is the chemical reaction between carbonic acid (H₂CO₃), resulting from a combination of atmospheric carbon dioxide (CO₂) with water. And calcium ion (Ca²⁺) from dissolution of hydrated cement products such as calcium hydroxyl Ca(OH)₂, calcium silicate hydrates (C-S-H) and calcium aluminates hydrates (C-A-H). This results in the formation of calcium carbonate (CaCO₃), as shown in Eqs. 1 to 4 (Neville, 2011; Tarun and Rakesh, 2010).



The durability of concrete structures is controlled by their capacity to delay ion and fluid transport inside concrete. The transport properties of concrete are

represented through permeability of concrete, which is likely to be significantly affected by the formation of cracks. Cracks in concrete structures are predictable in reinforced concrete members due to the weakness of tension capacity in concrete. Cracks maybe either non-structural or structural. Structural cracks have a tendency to be wider (> 0.1 mm) while non-structural cracks are commonly finer.

Structural cracks, or cracks due to stress, are typically produced due to excessive loading, low strength of concrete, inadequate reinforcement, impact loading, or movement of foundations, or a combination of these factors. On the other hand, non-structural cracks may occur due to: plastic shrinkage cracks, early-age thermal shrinkage, drying shrinkage and external chemical attack or carbonation shrinkage (Neville, 2011). The carbon dioxide penetration and reaction with hydrated cement-based products often lead to carbonation shrinkage in concrete structures. It is a physio-chemical change in concrete that causes an increment in weight and shrinking in volume (increment in density). This type of shrinkage is likely to generate shallow cracks on the concrete surface (Neville and Brooks, 2010).

The cracks in concrete influence the diffusivity of aggressive species affecting durability. However, current modelling methods for durability assessment often exclude the effect of cracks, voids and defects in concrete, such as corrosion initiation, thereby reducing their effectiveness in predicting the durability of concrete structures (Pacheco and Polder, 2010). Therefore, it is important to study and consider how the presence of cracks may affect the rate of carbonation in concrete structures. Moreover, carbonation negatively affects the concrete alkalinity and reduces the pH of concrete pores solution from 13 to 9 (Neville, 2011), which is a considerable factor accelerating the chloride penetration as well as the corrosion of reinforced concrete structures (Dyer, 2014; Broomfield, 2007).

Some studies have examined diffusion of deleterious substances through cracked concrete (Song *et al.*, 2006 and Jang *et al.*, 2011). All of these studies have concluded that cracks increase the total molar flux of gases/fluids through concrete. However, there is no agreement on how to model the movement of the carbonation front in cracked concrete.

The concept of effective diffusion of CO₂ or carbonation front based on the penetration of CO₂ through un-cracked and cracked concrete is proposed in this study. The CO₂ first penetrates the cracks within concrete, and then diffuses outwards into the sound un-cracked concrete in all directions. The focus of this paper is to examine the effect of size of cracks in reinforced concrete samples on the penetration depth of carbonation. The impact of replacing OPC cement by pulverized fuel ash (PFA) and ground granulated blast furnace slag (GGBS) on the carbonation depth in cracked concrete has also been investigated.

2.0 EXPERIMENTAL WORK

2.1 Materials

Portland Limestone cement (CEM II/A-LL 32,5R) was used in this project which has a specific gravity of 3.05. Chemical and physical properties of the cement satisfy the BS EN 197-part 1: 2011. Ground granulated blast furnace slag (GGBS) used in this study was produced by Hanson Cement, that satisfies the chemical and physical property requirements of BS EN 15167-part 1: 2006. Pulverized fuel ash (PFA) was obtained from CEMEX UK, that satisfies the requirements of BS EN 450-part 1: 2012. Natural sand was used, and coarse aggregate was crushed gravel with a size range of 5-14 mm. The grain size analysis, chloride and sulphate content satisfies BS 882:1983. Deformed or ribbed steel (B500A) (8mm) used to reinforce the concrete prisms to achieve the crack in samples and investigate the corrosion

condition. Mechanical properties of steel are in compliance with BS 4449:2005+A2:2009.

2.2 Concrete Mix Designs

To achieve various properties of concrete, different water to cement ratio and different cementitious materials such as ground granulated blast furnace slag (GGBS) and pulverized fly ash (PFA) were used. The GGBS and PFA can change micro-structure and strength of concrete (Neville, 2011). Building Research Establishment method was employed to design the mixes used in this study as shown in Table 1. The mixing method is important to obtain the required workability and homogeneity of the concrete mix by mechanical mixing.

Flexural method was used to induce the cracks; reinforced concrete prisms were used by fixing reinforcement in moulds with concrete cover 2 cm. Samples were cast in two layers. Each layer was vibrated using an electrical vibrating device to achieve the homogenous concrete and avoid the segregation of concrete. The specimens were demoulded and cured in a sink filled up with tap water until the time of testing or exposure to CO₂ environment condition at the age of 28 days.

Finally, the method of filling and preparation of moulds, compaction and levelling the surface of concrete, curing and transporting of samples were according to BS EN 12390 part-2:2009.

2.3 Methodology

The main objective of the study is to investigate the effect of the crack width on the carbonation in concrete structures. Therefore, cracked concrete prisms were designed and exposed to these parameters of carbonation environment. In this case, the flexural method was employed to induce the cracks in concrete samples as shown in Fig.1. Four different crack width ranges, (0, 0.05-0.15mm, 0.15-0.25mm and 0.25-0.35mm) were applied to 100*100*500 mm concrete prisms.



Fig. 1. Flexural method was used to create the crack in concrete sample

Table 1. Concrete mixes design according to method of Building Research Establishment (1988)

Mix symbol	w/(c +b)	Cementitious materials			Water kg/m3	Sand kg/m3	Gravel kg/m3
		kg/m ³					
		Cement	PFA	GGBS			
M 0.4	0.4	513	-	-	205	653	980
M 0.5	0.5	410	-	-	205	711	1023
M 0.6	0.6	350	-	-	205	711	1041
M 0.5 + 0.35 PFA	0.5	266	144	-	205	711	1023
M 0.5 + 0.30 GGBS	0.5	287	-	123	205	711	1023

The crack width was measured by microscope meter with accuracy 0.01 mm. The crack depth, D_{crack} , was computed by measuring the time of transfer of pulse velocity using the ultrasonic device according to the Eq.5 (Al-Samaraai & Raouf -1999) . Fig. 2 and 3 are illustrated the methods for crack width and crack depth measurement respectively. The reinforcement steel bar can control on crack width and depth in the concrete sample.

$$D_{crack} = x \sqrt{\frac{T_c^2}{T_s^2} - 1} \quad (5)$$

where:

x is specific distance, T_c is the transfer time through a cracked concrete distance(x), and T_s is transfer time through a sound concrete distance (x).

In this study, the specimens were exposed to accelerated environment conditions in carbon dioxide incubator. In particular, the surface of prisms was exposed to an environment with a CO₂ concentration of 5%, the temperature of 45 °C and relative humidity of 65% for 8 weeks. These samples were split into two parts using compression testing machine as designated by Al-Amoudi *et al.* (1991). The first part was sprayed using phenolphthalein solution (with one gram of phenolphthalein powder dissolved into a solution of 70 ml and 30 ml of ethanol and deionized water respectively according to CEN/TS 12390-10:2007) to indicate the carbonation depth. Whilst, the second face of the sample was drilled at the crack location in order to collect a concrete powder at different depth to find peak intensities for Ca(OH)₂ and CaCO₃ using XRD. Three samples were tested for every case, and average values are reported in this paper.

The concrete powder was collected from the exposed face at eight depth intervals; 0-6 mm, 6-12 mm, 12-18 mm, 18-24 mm, 24-30 mm, 30-36 mm and 36-42 mm and non-carbonation sample powder at depth 42-48 mm, using dry drilling equipment. The concrete powder was filtered using 150 micrometer sieve to reduce the amount of coarse grains resulted

from the aggregate, then dried in oven at 50°C for 24 hours, and then kept in sealed plastic bags till tested.

2.4 Tests for Concrete Sample

The compressive strength, ultra-sonic pulse velocity test, porosity and carbonation depth test by phenolphthalein indicator and XRD method are carried out for concrete under investigation. The porosity and compressive strength test were performed in accordance with ASTM C642:2013 and BS EN 12390, part 3:2000 respectively. The test procedure given in CEN/TS 12390-10:2007 was used to determine the carbonation depth by phenolphthalein indicator. The method proposed by Chang and Chen (2006) to measure the change in intensity of peaks for Ca(OH)₂ and CaCO₃ by XRD due to carbonation action is used on concrete powder samples.




Fig. 2. Microscope meter used to measure the cracks width




Fig. 3. Measuring the crack depth by pulse velocity of the ultrasonic device

3.0 RESULTS AND DISCUSSION

In this section, the results of the experimental work are presented and discussed. These results and their discussions are mainly focused on three aspects; the impact of water to cement ratio (representing strength of concrete), crack width, and supplementary cement materials on carbonation depth.

3.1 Carbonation Depth in Concrete Test

The Carbonation depth is a measure of diffusivity of carbon dioxide in concrete and reduction of alkalinity of pore water solution in concrete.

Carbonation Depth by Phenolphthalein Indicator

The carbonation depths as a function of crack widths for the mixes used in this study are presented in Figs. 4, 7 and 8. The results illustrate that the penetration of carbonation depth from the exposed surface increases significantly with the increase in crack width in concrete samples. The percentage increases in carbonation depth for samples having a crack with respect to the control concrete samples are presented in the Table 2.




Fig. 4. Effect of crack width and w/c ratio on carbonation depth for sample exposure to (CO₂= 5%, RH=65% and T=45 °C)

Table 2. Increase percentage in carbonation depth for cracked samples concerning un-cracked samples

Sample	Increase percentage in carbonation depth in samples with a crack width (%)		
	0.05 -0.15 mm	0.15-0.25 mm	0.25-0.35 mm
M 0.4	75	207	380
M 0.5	125	158	250
M 0.6	76	94	176
M 0.5+ GGBS	226	279	395
M 0.5+ PFA	54	81	104

The carbonation depth also increases with the increase in w/c ratio. The percentage increase in carbonation depth for mix with w/c 0.5 (M 0.5) and mix with w/c ratio 0.6 (M 0.6) in comparison to mix with w/c 0.4 (M 0.4) were (60%, 93%, 35% and 17%) and (127%, 114%, 43% and 31%) respectively for samples having crack width (0, 0.05-0.15mm, 0.15-0.25mm and 0.25-0.35mm).

The effect of compressive strength (which is a function of w/c ratio) on the carbonation depth is depicted in Fig. 5. The increase in carbonation depth for controlling concrete mixes with the increase in compressive strength is due to the increase in the volume of permeable voids that help CO₂ penetration. Furthermore, key factor controlling carbonation rate is the diffusivity of the hardened cement paste, which is a function of the pore system of the hardened cement paste during the period when the diffusion of CO₂ takes place (Neville, 2011). The rate of carbonation is inversely proportional to the strength of concrete without supplementary materials (Roy *et al.*, 1999). The results of the un-cracked concrete sample (without GGBS and PFA) were well-matched with (Chi *et al.*, 2002). The porosity and compressive strength of concrete have a significant impact on carbonation depth as shown in Fig.5 and 6. From these figures, a relationship is proposed between the carbonation depth in concrete vs the compressive strength and porosity (also shown in Eq. 6 and 7);

$$x = -31.6 \ln f_{cu} + 133.7 \quad R^2 = 0.98 \quad (6)$$

$$x = 0.034e^{0.535\epsilon} \quad R^2 = 0.97 \quad (7)$$

where:

x= carbonation depth in mm;

f_{cu}= compressive strength in MPa

ε = porosity in %.




Fig. 5. Effect of compressive strength on carbonation depth for sample exposure to (CO₂= 5%, RH=65% and T=45 °C)




Fig. 6. Effect of porosity on carbonation depth for sample exposure to (CO₂= 5%, RH=65% and T=45

Table 3.Effect of compressive strength and porosity and carbonation depth for mixes used in the study

Sample	w/c	Carbonation depth	Comp. strength MPa	Porosity %
M 0.4	0.4	8	53.2	10.1
M 0.5	0.5	12	48.1	11.1
M 0.6	0.6	17	39.7	11.5
M 0.5+ GGBS	0.5	15	47.2	10.1
M 0.5+ PFA	0.5	26	31.6	10.1

The results also show that the carbonation depth of these mixes is higher than the carbonation depth for a mix without these materials. This can be linked to the reduction of Ca(OH)₂ that is consumed by the supplementary cementing material to produce C-H-S gel and CaCO₃ (Roy and Indorn,1982) as shown by Eqs. 1 to 4.

This reduction is accompanied by the reduction of pH, as picked up by phenolphthalein indicator used for these experiments. Hence, the carbonation depth in M 0.5+PFA is the highest due to more consumption of Ca(OH)₂ as can be seen by XRD analysis results in the next section.

Consequently, it is observed from the results that the carbonation depth within un-cracked areas of concrete (away from the discrete cracks) is considerably less than the carbonation depth in un-cracked control samples; Fig. 8a (un-cracked sample) have mean carbonation depth of 26 mm versus Fig. 9a (cracked sample) have mean carbonation depth of 18 mm. This has not been reported in the previous literature, and the reasons for this are being investigated in detail.




Fig. 7. Effect of crack width on carbonation depth for sample exposure to (CO₂= 5%, RH=65% and T=45 °C)




Fig. 8. Carbonation depth of mixes used in the study




Fig. 9. Effect of crack on the diffusion of CO₂ and reduction in PH level in concrete

Finally, Fig. 10 illustrates the corrosion of rebars focused at the crack location. The cracks encourage deeper penetration of CO₂, which reacts with calcium hydroxide in the hydrated cement matrix to form calcium carbonate and decreases the pH of concrete surrounding the rebars (Tarun and Rakesh, 2010). This also provides an easy path to transport moisture and oxygen hence accelerates corrosion at the crack locations.

Carbonation Front by X-Ray Diffraction

As mentioned previously, the carbonation process consumes the Ca(OH)₂ by converting to CaCO₃. In order to identify the impact of CO₂ diffusivity on the change in mineralogical composition, X-ray diffraction analysis (XRD) was employed. The concrete powder was collected from the exposed face at seven depth depths. The results of control specimen and cracked concrete samples are shown in Fig. 11; some changes in relative intensities of crystalline phases (peaks) with the depth of carbonated concrete have been detected. The change in peak intensity would be attributed either to a change in the degree of crystallization of the specified phase and a change in its quantity.

The noticeable change in mineralogical composition due to carbonation might have an impact on the physical and chemical properties of carbonated concrete (Dyer 2014). The relative intensity or main peaks of Ca(OH)₂ are noticed at angles of diffraction (2θ) 18.1° and 34.1° (International Center for Diffraction Data, ICDD). It reduces or disappears as the degree of carbonation increases in the samples. On the other hand, the intensity of CaCO₃ phase for the main peak can be detected at an angle of diffraction (2θ) 29.39°, which increases in the samples with the increase in carbonation depth.



Fig.10. Corrosion of reinforcement bar at the location of a crack due to exposing to CO₂ with 65% of RH

The changes in the amount of CaCO₃ and Ca(OH)₂ can be observed through the changes in the peaks obtained from the XRD analysis Chang and Chen (2006). Graphs showing the relative intensity of X-Ray Diffraction at various concrete depths for different mixes used in this study (for both cracked and un-cracked samples) are shown in Fig. 12.

The depth of carbonation is represented in the literature using two distinct parameters, X_p and X_f . The depth of carbonation, X_p relates to the depth where concrete is considered fully carbonated and the pH of pore water in concrete is about 9 (Neville, 2011). The depth of carbonation front X_f relates to the depth beyond which concrete is yet unaffected by the carbonation. At this depth, the pH of pore water of concrete maintains an original pH of concrete, which is around 13. The zone between X_p and X_f can be considered partially carbonated with pH value varying between 9 and 13.

X_p have been obtained from Fig. 4 and 7, using phenolphthalein indicator. Whereas X_f can be taken as the point on the graphs of the relative Intensity X-Ray Diffraction curve where the curve of for Ca(OH)_2 becomes horizontal (i.e. no further change in Ca(OH)_2 beyond this depth is expected). The X_p and X_f depth for concrete samples are presented in Fig.12 and Table 4.

Both cracked and un-cracked samples are presented in in Fig.12 and Table 4. In most cases of un-cracked

concrete samples, the carbonation front depth, X_f is approximately twice of the depth of fully carbonation depth, X_p , which confirms the results of Chang and Chen (2006). In cracked concrete samples, on the other hand, the above relation do not hold true and the difference between X_p and X_f is considerably smaller than the case of un-cracked concrete, which agrees with the results of Park (2008) for un-cracked concrete samples.




Fig. 11. Carbonation depth investigated by XRD,(a) Sample of M 0.6-0.25 mm is taken from the surface (b) sample is taken from depth 40mm (un-carbonated), Q=Quartz, F= feldspar, CH= Ca(OH)_2 and CCO3= CaCO_3

Table 4. Carbonation depth and front according to intensities of XRD for samples

Crack width	Carbonation depth and front (mm)							
	0		0.05-0.15mm		0.15-0.25 mm		0.25-0.35 mm	
Sample	X_p	X_f	X_p	X_f	X_p	X_f	X_p	X_f
M 0.4	8	32	14	23	23	30	36	43
M 0.5	12	25	27	33	31	40	42	47
M 0.6	17	34	30	35	33	36	47	52
M 0.5+GGBS	15	30	31	38	36	42	47	52
M 0.5+PFA	26	52	40	45	47	52	50	53

4.0 CONCLUSIONS

This study investigates the effect of cracks caused by loading on the carbonation depth. Carbonation depth was determined using an accelerated environment test programme by Phenolphthalein Indicator and XRD analysis. Carbonation depth X_p and X_f depth have been determined by Phenolphthalein Indicator, while the carbonation front has been measured by XRD analysis. The effect of replacing OPC cement by

(PFA) (GGBS) on the carbonation depth in cracked concrete was also investigated. The following conclusions can be drawn from the results;-

- 1) The crack width significantly increases the carbonation depth for all mixes used in the study.
- 2) Carbonation rates in the vicinity of the cracks are considerably higher due to relatively faster penetration of CO_2 into the crack followed by orthogonal outward diffusion into the un-cracked concrete surrounding the crack.




Fig. 12. Relative intensity of XRD analysis for CaCO₃ and Ca(OH)₂ in concrete sample (un-cracked and cracked 0.25-0.35 mm) exposure to CO₂ for 8 weeks

- 3) XRD investigation made it possible to gain a better understanding of the mineral- structural changes induced due to exposure to the CO₂ environment. Results from the XRD investigation also helps in identifying areas of fully carbonated and un-carbonated concrete in greater detail including the partially carbonated zones.
- 4) The type of binding materials has a vital role on carbonation depth, whereby the replacement of OPC by supplementary cementing materials such as PFA and GGBS have a significant increase in the penetration of carbonation in concrete.
- 5) The carbonation depths, X_p and front X_f , are affected by the material behaviours such as porosity, compressive strength and due to impact of diffusivity of CO₂.

References

- AL-Amoudi, O., Rasheeduzzafar and Maslehuddin, M. 1991. Carbonation and corrosion of rebars in salt-contaminated OPC/PFA concretes. *Cement and Concrete Research*, 21, 38-50.
- Al-Samaraai, M. and Raouf, Z. 1999. Non-destructive tests for concrete. Sharqi University, UEA.
- ASTM C642:2013, Density, Absorption, and Voids in Hardened Concrete.
- British Committee for Standardization, BS 4449:2005+A3:2016. Steel for the reinforcement of concrete. Weldable reinforcing steel. Bar, coil and decoiled product.
- British Committee for Standardization, BS 812-103.1-1985. Testing aggregates — Part 103: Methods for determination of particle size distribution.
- Broomfield, J.P., 2007. Corrosion of steel in concrete. 2nd edition. London. Taylor & Francis.
- Chang, C., Chen, J. 2006. The experimental investigation of concrete carbonation depth. *Cement and Concrete Research* Vol. 36, pp. 1760–1767.
- Dyer, A., 2014. *Concrete durability*. New York: Taylor & Francis Group, LLC.
- BS EN 12390 part- 2:2009. Testing hardened concrete –; Part 2: Making and curing specimens for strength tests.
- BS EN 12390, part 3:2000. Testing hardened Concrete Part 3: Compressive strength of test specimens.
- BS EN 15167-part 1: 2006. Ground granulated blast furnace slag for use in concrete, mortar and grout — Part 1: Definitions, specifications and conformity criteria. British Standard Institution.
- BS EN 197-part 1: 2011. Cement-part 1: Composition, specifications and conformity criteria for common cements.
- BS EN 450-part 1: 2012. Fly ash for concrete Part 1: Definition, specifications and conformity criteria.
- Chi, J. M., Huang, R. and Yanlg, C. C., 2002. Effect of Carbonation on Mechanical Properties and Durability of Concrete Using Accelerating Testing Method. ; *Journal of Marine Science and Technology*, 10(1), pp. 14-20.
- European Committee for Standardization, DD CEN/TS 12390-10:2007. Testing hardened concrete. Determination of the relative carbonation resistance of concrete.
- Jang, S.Y., Kim, B.O. and Oh, B.H. 2011. Effect of crack width on chloride diffusion coefficients of concrete by steady-state migration tests. *Cement and Concrete Research*, 41(1), pp.9–19
- Kwon S., Na U., Park S. and Jung S. 2009. Service life prediction of concrete wharves with early-aged crack: Probabilistic approach for chloride diffusion. *Structural Safety*, 31 (2009) pp. 75–83.
- Lagerblad, B. (2005). Carbon dioxide uptake during concrete life cycle-state of the art. CBI Report 2:2005, Swedish Cement and Concrete Research Institute, SE-100 44, Stockholm.
- Neville, A.M., 2011. *Properties of concrete*. (Five and Truly Final Edition) London: Pearson Education Limited.
- Neville, A.M., Brooks, J.J. 2010. *Concrete Technology*. (Second Edition) London: Pearson Education Limited.
- Pacheco, J. and Polder, R. 2010. Corrosion initiation and propagation in cracked concrete – a literature review. Proceedings of the 4th International RILEM PhD Workshop, Madrid, Spain.
- Park, D. 2008. Carbonation of concrete in relation to CO₂ permeability and degradation of coatings. *Construction Building Materials*, 22(11) pp.2260–2268.
- Roy, D.M., and Indorn, G.M., 1982. Hydration, Structure and Properties of Blast Furnace Slag Cement, Mortar and Concrete, *ACI Journal*, Nov.-Dec. 1982, pp. 444-457.
- Roy, S, Poh, K and Northwood, D, 1999. Durability of concrete accelerated carbonation and weathering studies. *Building and Environment*, 34. (5), pp. 486-595.
- Song, H., Kwon, S., Byun, K. and Park, C., 2006. Predicting carbonation in early-aged cracked concrete. *Cement and Concrete Research*, 36(5), PP. 979–989.
- Tarun R. and Rakesh, K. 2010. Global warming and cement –based materials. UWM Center for By-Products Utilization, Milwaukee, Wisconsin USA.