

SESSION 6: LIGHT ALLOYS, MARITIME HALL

Co-Chairs: Qigui Wang, General Motors Company Pontiac; Tongmin Wang, Dalian University of Technology; Jianxin Zhou, Huazhong University of Science and Technology; Lianxi Hu, Harbin Institute of Technology

SATURDAY, OCTOBER 15, 2016

Corrosion inhibition of 7150 Al alloy in the presence of some amino acids – molecular dynamics simulation, quantum chemical, and electrochemical studies

Qingqing Sun; Qingyou Han, Purdue University; Jie Li; Russell Russell Sun, Central South University

ABSTRACT

Inhibition performance of three amino acids, namely L-phenylalanine (Phe), L-methionine (Met), and L-histidine (His) as corrosion inhibitors for 7150 Al alloy surface in 0.1M HCl + 1M NaCl solution was investigated using cyclic polarization test, quantum chemistry calculation, and molecular dynamics (MD) simulation. A significant decrease in the corrosion rate of alloy was observed in the presence of the amino acids. The inhibition efficiency is in the following decreasing order under all studied temperatures: Phe < Met < His, as revealed by the electrochemical results. From the calculated binding energies by MD, His shows preferred adsorption on the alloy surface among the three tested amino acids, showing good consistent with electrochemical data. Quantum chemistry calculations were performed under water–metal interface conditions with dielectric constant equals 6. The results showed that quantum chemistry parameters such as dipole moment values, E_{HOMO} , and $E_{\text{LUMO}} - E_{\text{HOMO}}$ might not be able to show good agreement with experimental inhibition efficiency. However, the adsorption sites of the studied inhibitors can be determined using Fukui indices and Mulliken charges of the local atoms, as calculated through quantum chemistry method.

KEYWORDS: 7150 Al alloy, amino acids, corrosion inhibition, quantum chemistry, molecular dynamics, cyclic polarization