**PERFORMANCE DATA FOR SOME
BITUMINOUS CONCRETE OVER-
LAYS IN INDIANA**

JUNE, 1957

NO. 18

**Joint
Highway
Research
Project**

**PURDUE UNIVERSITY
LAFAYETTE INDIANA**

by
**W. H. GOETZ
J. F. MCLAUGHLIN**

PERFORMANCE DATA FOR SOME
BITUMINOUS CONCRETE OVERLAYS IN INDIANA

TO: K. B. Woods, Director
Joint Highway Research Project

June 12, 1957

FROM: Harold L. Michael, Assistant Director

File: 2-11-3
Project No. C-36-31C

Attached is a technical paper entitled, "Performance Data for Some Bituminous Concrete Overlays in Indiana," by Professors W. H. Goetz and J. F. McLaughlin.

This paper was presented at the 43rd Annual Purdue University Road School in April, 1957, and will be submitted for publication in the Proceedings.

This paper is a summary of the studies to-date on the performance of bituminous concrete overlays in Indiana. The paper includes initial work on a laboratory study that evaluates the plastic nature of a bituminous mixture under repeated application of load.

Respectfully submitted,

Harold L. Michael

Harold L. Michael, Assistant Director
Joint Highway Research Project

HLM:hgb

Attachment

cc: D. S. Berry	J. F. McLaughlin
A. K. Branham	H. L. Michael
J. R. Cooper	R. D. Miles
W. L. Dolch	R. E. Mills
W. H. Goetz	B. H. Petty
F. H. Green	C. E. Vogelgesang
J. T. Hallett	J. L. Waling
F. F. Havey	J. E. Wilson
G. A. Hawkins	K. B. Woods
G. A. Leonards	E. J. Yoder

PERFORMANCE DATA FOR SOME
WITTINGTON CONCRETE OVERLAYS IN INDIANA

For E. E. Hodge, Director
Joint Highway Research Project

From Harold L. Michael, Assistant Director
Project No. 0-10-110
Date 12, 1957

Enclosed is a technical paper entitled, "Performance Data for
Some Wittington Concrete Overlays in Indiana," by Professor H. L.
Goetz and E. E. Hodge.

This paper was prepared as the first Annual Joint Highway
Research Project in 1957, and will be submitted for publication in
the Proceedings.

This paper is a summary of the studies made on the performance
of Wittington concrete overlays in Indiana. The paper includes initial
work on a laboratory study of Wittington concrete overlays and a
summary of the field studies.

Very truly yours,

Digitized by the Internet Archive
in 2011 with funding from

LYRASIS members and Sloan Foundation; Indiana Department of Transportation

Wittington

Association

1	Wittington
2	Wittington
3	Wittington
4	Wittington
5	Wittington
6	Wittington
7	Wittington
8	Wittington
9	Wittington
10	Wittington
11	Wittington
12	Wittington
13	Wittington
14	Wittington
15	Wittington
16	Wittington
17	Wittington
18	Wittington
19	Wittington
20	Wittington

TECHNICAL PAPER

PERFORMANCE DATA FOR SOME
BITUMINOUS CONCRETE OVERLAYS IN INDIANA

by

W. H. Goets
Research Engineer

and

J. P. McLaughlin
Research Engineer

Joint Highway Research Project
Project No. C-36-31C
File: 2-11-3

Purdue University
Lafayette, Indiana

June 12, 1957

TECHNICAL PAPER

PERFORMANCE DATA FOR SOME
BITUMINOUS CONCRETE OVERLAYS IN INDIANA

by

W. H. Goets
Research Engineer
and
J. F. McLaughlin
Research Engineer

Joint Highway Research Project
Project No. 2-11-3
File: C-36-31C

Purdue University
Lafayette, Indiana

June 12, 1957

PERFORMANCE DATA FOR SOME BITUMINOUS CONCRETE OVERLAYS IN INDIANA

Introduction

The bituminous concrete most used by the State of Indiana has been included in the standard specifications without essential change as to type at least since 1934. Until about 1948, this material was used primarily as the surfacing layers of high-type flexible pavements. In this application, the performance of the material was considered to be entirely satisfactory and the stability of the mixture was not questioned.

Since 1948, however, this bituminous mixture type has been used more and more for the resurfacing of deteriorated portland cement concrete pavements. Also, in the period following the war and particularly in the last several years, the number and weight of heavy vehicles using Indiana highways has increased markedly. This change in the use of the material, coupled with the large increase in traffic might be expected to create problems that did not exist previously.

The bituminous-concrete overlay that has been used in Indiana usually is composed of two layers: (1) a binder or leveling course which has a maximum aggregate size of three quarters to one-inch, 65 percent coarse aggregate (material retained on the No. 6 sieve), 35 percent fine aggregate (essentially none of which passes the No. 200 sieve), and which contain 4.5 to 4.5 percent asphalt by weight of the mixture, and (2) a surface course which has a maximum aggregate size of 1/2-inch, about 50 percent coarse aggregate, 50 percent fine aggregate and with about 3 percent of the total passing the No. 200 sieve. It usually contains 6.0 to 7.0 percent asphalt by weight of the mixture. The thickness to which each of the courses is laid is variable depending upon the condition of the road to be resurfaced, the expected traffic intensity and perhaps other factors, but a total thickness of 2-1/2 inches composed of 1-1/2 inches of binder and 1-inch of surface is not uncommon. The asphalt cement used is a 60-70 penetration grade.

The performance of Indiana's AH-binder and Type B surface as an overlay for Portland cement concrete has been the subject of much investigation in the past several years. The purpose of this paper is to summarize some of the results of a number of the field studies that have been made which deal with such things as the effect of thickness of lay and compaction. In addition, examples of some of the specific problems that have been encountered when using this type of mixture for an overlay are illustrated and steps that have been taken to solve the problems are enumerated. Finally, the current research on this subject is discussed by briefly describing some of the work in progress at the Joint Highway Research Project Laboratories.

Experimental Overlay - S R 37

Thickness design was a variable which was included in the construction of an overlay on State Road 37 between Elwood and Noblesville. This overlay built in 1950 has a standard thickness design of about 2-1/2 inches composed of 150 pounds per square yard of binder and 100 pounds per square yard of surface. On sections 1,000 feet in length other thicknesses were employed as follows:

1. About 2 inches total, composed of 100 pounds per square yard of binder and 100 pounds per square yard of surface.
2. About 3 inches total, composed of 150 pounds per square yard of binder and 150 pounds per square yard of surface.
3. About 4 inches total, composed of 300 pounds per square yard of binder and 100 pounds per square yard of surface.

Concrete pavement with both jointed and non-jointed slab design is included in this part of State Road 37 and these experimental overlays of various thicknesses were constructed on each in order to study the effect of the type of concrete pavement on the performance of the resurfacing.

This overlay on State Road 37 is now almost seven years old and, except for the presence of reflection cracks, the performance is satisfactory. Figure 1 shows a view of the road on the jointed concrete section. This is a good example of the successful use of this type of overlay under moderate to heavy moving traffic conditions. Figure 1 and subsequent illustrations showing condition of this road (Figures 2 to 4) are from pictures which were taken in March, 1957 when the overlay was about seven years old.

Effect of Overlay Thickness

All thickness designs on this road did not perform equally and there is evidence that heavy lays may be advantageous for some conditions. In Figure 2, for example there is shown for the jointed concrete pavement a "typical" reflection crack in the four-inch thick overlay on the left compared to a typical one in the two-inch thick overlay on the right. The crack in the two-inch thick overlay is more severe. It follows along the line of the joint and really is a system of multiple cracks with chunks of bituminous-concrete mixture beginning to be cracked off. The crack in the four-inch thick overlay, however, is a meandering one. It is, for the most part, a single crack and there are no signs of ravelling associated with it.

Figure 1. Bituminous Concrete Overlay on State Road 37.

COMPARISON OF PERFORMANCE OF 2" AND 4" THICK
OVERLAY ON JOINTED CONCRETE

SR 37

FIG. 2

Figure 3 shows a similar comparison for the bituminous-concrete overlay placed on the concrete pavement without transverse joints. This concrete has a fairly short crack interval. Before and after surveys indicated that most of the cracks in the concrete were reflected in the overlay. It may be seen from Figure 3, however, that these cracks are generally much less severe than those in the jointed concrete section. Again, the performance of the four-inch thick overlay is compared with the two-inch thick one with the four-inch thick section on the left. The condition of the cracks indicates some advantage for the thicker lay. But the difference is not as great as for the case with jointed concrete pavement.

A comparison between the performance of the three-inch thick overlay on jointed and non-jointed concrete is shown in Figure 4. The jointed concrete is on the left and the non-jointed concrete is on the right. For this thickness, which is very close to the standard design for the road, it is seen again that reflection cracking is less severe over non-jointed concrete.

Density Studies

Several additional studies were made on this section of State Road 37, one of which had to do with compaction of the bituminous concrete and subsequent densification of the mixture from traffic action. Samples of the mixture were obtained soon after construction from areas of the pavement which were in the wheel tracks of a traffic lane and from areas between the wheel tracks. These samples were taken in each of the three thickness designs and from the test sections on both jointed and non-jointed concrete. Also, the sampling was duplicated for the north-bound and south-bound traffic lanes. Density determinations were made on all samples. This procedure was repeated when the overlay was two years old and again when the overlay was five years old.

COMPARISON OF PERFORMANCE OF 2" AND 4" THICK OVERLAY
ON NON-JOINTED CONCRETE

SR 37

FIG. 3

COMPARISON OF PERFORMANCE OF 3-INCH THICK, OVERLAY
ON JOINTED AND NON-JOINTED CONCRETE

SR 37

FIG. 4

Table 1 shows the results of the first and second samplings tabulated so that a comparison may be made of density in the wheel tracks versus that between the wheel tracks. These results show binder and surface density values to be similar. In addition, it may be said that there appears to be no practical difference between the density results of the samples taken from the wheel tracks compared to those taken between the wheel tracks. Naturally, year to year differences are highly significant and these results show how a pavement densifies with repeated loads. They also show a trend toward uniformity of density that did not exist immediately after construction.

While considering practical and significant differences it should be recorded that analyses of variance were performed on the density results shown in Table 1. These analyses showed statistical significance over the whole table but, as sometimes happens, the differences declared to be significant by the analysis were not thought to be so in a practical sense. Subsequent observation of the road in succeeding years has justified this evaluation.

Tables 2 and 3 show two comparisons of the results for the three sampling periods. Table 2 shows a comparison of density values for various thickness designs over jointed and non-jointed concrete and Table 3 shows a similar comparison for the thickness designs in the north-bound and south-bound lanes. These density values in Tables 2 and 3 are for the combined binder and surface. Comparisons indicate that neither lane position nor concrete design appeared to affect the densification of the mixture in service.

Table 1

Density Test Results - Experimental Overlay, S R 37

Comparison of Density In and Between Wheel Tracks

Pounds Per Cubic Foot

Layer	Age	Position	Thickness Design			Average
			300# Binder 100# Surf.	150# Binder 150# Surf.	100# Binder 100# Surf.	
Binder	0 to 3 Mos.	Wh. Trk.	141.4	139.8	139.5	140.2
		Bet. Trk.	141.0	138.4	139.2	139.5
	2 Yrs.	Wh. Trk.	145.4	145.2	145.2	145.3
		Bet. Trk.	145.4	144.6	145.0	145.0
Surface	0 to 3 Mos.	Wh. Trk.	138.9	142.9	139.2	140.3
		Bet. Trk.	139.5	144.4	139.6	141.2
	2 Yrs.	Wh. Trk.	146.4	146.6	144.7	145.9
		Bet. Trk.	145.1	147.4	145.3	145.9

Table 2

Density Test Results -- Experimental Overlay, S. R. 37

Comparison of Density Over Jointed and Non-Jointed Concrete

Pounds Per Cubic Foot

Age	Concrete Type	Thickness Design			Average
		300# Binder 100# Surface	150# Binder 150# Surface	100# Binder 100# Surface	
0-3	Jointed	141.2	141.6	137.3	140.1
Mos.	Non-jointed	139.3	141.2	141.5	140.7
2	Jointed	146.0	144.7	143.9	144.9
Yrs.	Non-Jointed	145.2	146.9	146.3	146.1
5	Jointed	147.3	147.9	145.9	147.0
Yrs.	Non-jointed	147.2	147.5	147.7	147.5

Table 3

Density Test Results - Experimental Overlay, S. R. 37

Comparison of Density in North and South-Bound Lanes

Pounds Per Cubic Foot

Age	Lane	Thickness Design			Average
		300# Binder 100# Surface	150# Binder 150# Surface	100# Binder 100# Surface	
0-3 Mos.	N.-Bound	140.1	141.3	139.0	140.1
	S.-Bound	140.4	141.4	139.8	140.5
2 Yrs.	N.-Bound	146.6	145.7	144.9	145.7
	S.-Bound	144.6	146.2	145.4	145.4
5 Yrs.	N.-Bound	147.6	147.7	146.8	147.4
	S.-Bound	146.9	147.8	146.9	147.2

Table 4 shows the results of the density tests for each thickness design and age and for each of the two separate positions, wheel track and between wheel tracks. The results shown are averages over samples from both the jointed and non-jointed sections and from both northbound and southbound traffic lanes. We may make this type of comparison since results shown in Tables 2 and 3 indicate that the density of the mixture was not influenced by concrete design nor by location in either traffic lane.

There are several interesting comparisons that may be made from these data. First, it can be seen that for any age and for each of the three thicknesses the density of the mixture in the wheel tracks is not substantially different from that between the wheel tracks. This may not be too surprising for the earlier stages Table 1, but it was surprising to find that this homogeneity persisted for five years. It gives some indication concerning the plastic nature of this mixture. This plasticity has caused some distress in other locations, some illustrations of which are shown in Figures 5 through 8.

In addition to the homogeneity of density, a simple calculation will show that over the five-year period there was an overall increase in density of approximately 5 percent. We would consider this to be rather high, especially considering that the base point for these calculations was a density that already included the effect of a month or two of traffic. It would appear that greater densification during construction would be desirable. This matter is of extreme importance for realistic bituminous mixture design to serve severe traffic conditions.

Table 4

Density Test Results

Experimental Overlay-S.R. 37

Summary Comparison

Pounds Per Cubic Foot

Age	Position	Thickness Design		
		300# Binder 100# Surface	150# Binder 150# Surface	100# Binder 100# Surface
0-3 Mos.	Wh. Trk.	140.1	141.3	139.4
	Bet. Trk.	140.2	141.4	139.4
2 Years	Wh. Trk.	145.9	145.9	145.0
	Bet. Trk.	145.3	146.0	145.1
5 Years	Wh. Trk.	147.6	147.9	147.2
	Bet. Trk.	147.0	147.5	146.5

Figure 5. Overlay Performance at Intersection

Figure 6. Concrete Exposed by Rutting

Figure 7. "Flow" of Bituminous Concrete

Figure 8. Trench Cut in Bituminous Overlay

Overlay Performance Under Heavy Traffic

The progressive densification and performance of several overlays in the Calumet Area of the State also have been studied. The data from these locations are similar to those that were obtained from State Road 37. The results of density tests made on cores taken at these locations are shown in Table 5.

In this case data are available from only two early samplings of these locations, but the trend appears to be similar to the previous one. The comparison between wheel-track and non-wheel-track positions has been omitted in this case because it again was found to be non-significant. These locations are under observation and another sampling is scheduled for the fall of 1957.

As was previously indicated, some problems have arisen in connection with the performance of these bituminous concrete overlays which in specific locations have assumed severe proportions. Some of these problems are shown in Figures 5 through 8.

Evidence of lack of stability of some mixtures in some service conditions has been the development of ruts in the overlay in the wheel-track areas. This rutting, first investigated in the field in late 1953, was found to be present to some extent in many locations. It was present to an extent that could definitely be judged to be objectionable, however, in relatively few areas, each of which was subjected to much heavy, relatively slow-moving traffic. The condition was found to be the most severe at signalized intersections where the pavement and the overlay were subjected to stresses from braking traffic and to static loads.

An example of this is shown in Figure 5 which is a view looking west

Table 4

Density Test Results
Bituminous Concrete Overlays
In Calumet Area
Pounds Per Cubic Foot

Age	Location No. 1	Location No. 2	Location No. 3
1 to 3 Months	145.7	144.6	143.8
1 Year	149.6	150.0	148.5

at the westbound lanes of U. S. 12 and 20 near its intersection with Seventh Avenue just east of Gary. This picture was taken in November, 1953, at which time the overlay was three years old. The fact that the mixture had been subject to plastic movement seems evident from the pavement edge. The ruts were of the order of magnitude of a tenth of a foot. The mixture was literally being squeezed aside under the action of the wheel loads.

The same intersection in March, 1957, is shown in Figure 6. This view was taken just across the road from the previous one. The marks in the wheel track areas are not mud or patches, they show the underlying concrete. In this instance, the rutting has progressed to the ultimate. The entire thickness of the mixture has been displaced.

It took at least two years for much evidence of instability to show in the case illustrated in Figures 5 and 6. On another occasion the period was only a few months. Figure 7 shows a view looking south on Indianapolis Boulevard from the intersection with 151st Street in East Chicago. Again, the plastic nature of the mixture is illustrated by the apparent flow of the bituminous concrete.

Other locations in the State where extremely severe traffic conditions exist have shown similar results. Figure 8 shows one of two trenches cut for the full depth of the resurfacing across the outside lane of pavement on U. S. 40 near Indianapolis. The pavement distortion can be seen both from the cut face of the trench and from the water on the pavement which is ponded in the ruts in the wheel-track areas. This trench was cut approximately 750 feet back from the nearest signalized intersection. Another trench cut at the intersection showed more distortion than the case illustrated.

This trenching operation, in addition to enabling one to measure rutting, showed that the overlay had spread out in a transverse direction so that it

extended some six inches beyond the edge of the concrete to which it was placed during construction. Secondly, it was found from an examination of the sawed face that both the binder and surface layers were distorted in the wheel-track areas. Thirdly, and this is illustrated in Figure 9, it was found from density measurements made on samples taken at closely-spaced intervals across the traffic lane that the density of the mixture was essentially the same regardless of sample position.

In Figure 9 are grouped the density data for two-foot intervals across the trench. The low value that was observed near the pavement edge includes some samples that were obviously under-compacted.

All of these facts lead to the conclusion that the failures under consideration were caused by plastic flow. The realization of these failures and their nature lead the Indiana Highway Department to modify their bituminous concrete by several approaches. Asphalt content generally has been reduced in both the binder and surface layers. In some instances, the maximum aggregate size of the binder has been increased and the thickness of this layer increased with a corresponding decrease in surface-layer thickness. In other instances the ratio of coarse aggregate to fine aggregate has been increased in both the binder and the surface. Perhaps these modifications will provide the solution. There have been overlays built incorporating one or more of these modifications which appear to be performing quite satisfactorily at the present time under severe service conditions.

An example of this is a section of Indianapolis Boulevard which was resurfaced in 1954 and which carries the traffic of U. S. 12, 20 and 41. This overlay, at the time of this writing is almost three years old and appears to be in excellent condition in spite of the rather severe service exposure.

Figure 9.

Laboratory Research

In spite of this apparent satisfactory performance to date, however, it may be that an entirely new design concept is needed, if not immediately, then perhaps in the not too distant future. But accompanying a new or even modified design concept must be a better method of evaluating the mixture in the laboratory. The presently accepted strength tests for bituminous mixtures appear to be inadequate in certain cases.

For example, the mixture that rutted under traffic action until the underlying concrete showed through will meet the stability requirements of most of the standard acceptance tests. Yet under some service conditions the mix is obviously overly plastic. Highway engineers are particularly concerned with obtaining a laboratory test method which would overcome the inadequacies of the present methods. There is a need for a test which would be capable of evaluating the plastic nature of a bituminous mixture under repeated applications of load. It is toward this goal that our current research work has been directed.

The equipment and test set-up that we have been using to measure the deformation characteristics of a bituminous-concrete specimen under repeated applications of load is shown in Figure 10. Basically, this apparatus consists of an air motor mounted in a loading frame. Suitable valves and controls are present to admit compressed air to the air motor for a time interval which may be pre-set. The load is transmitted from the air motor to a shaft which in turn transmits load to the specimen. At the end of the pre-set time interval, during which the load is maintained constant, the inlet air valve to the motor closes and an exhaust valve opens, releasing the air, and hence quickly removing the load from the specimen. After another time interval which can also be pre-set, the cycle is automatically repeated. One can make

Figure 10. Repeated Load Test Apparatus

this sort of test at various temperatures and with various loads. As the specimen is repeatedly loaded it accumulates a permanent deformation which may be comparable to the tendency to rut that has been observed.

By keeping a record of the accumulation of this permanent deformation during the test, one may plot a graph of the sort shown in Figure 11. In this figure is shown a plot of log cumulative permanent deformation on the vertical scale versus the logarithm of the number of load repetitions on the horizontal scale. This particular illustration is from tests on two and four-inch thick cores of AH-Binder and Type B surface tested at 140° F and under a contact pressure of 200 psi. Without going into any detail, we will comment only that it is believed that the slope of these lines and the point on the line at which the data begin their upward deviation may have some significance with respect to the potential ability of the mixture to withstand repeated applications of load. This test method is still in the development stage but it shows great promise. Perhaps at some future Road School there will be further progress to be reported on this subject.

Figure 11.

BIBLIOGRAPHY

1. Goetz, W. H. and McLaughlin, J. F., "Progress Report No. 1 on Bituminous Concrete Resurfacing Study," A Report Presented to the Advisory Board, Joint Highway Research Project, Purdue University, July 29, 1954 (Unpublished).
2. Goetz, W. H. and McLaughlin, J. F., "Status of Project on Bituminous Resurfacing Mixtures," A Report Presented to the Advisory Board, Joint Highway Research Project, Purdue University, March 17, 1955 (Unpublished).
3. McLaughlin, J. F. and Goetz, W. H., "Results of Density Measurements on Bituminous Concrete Experimental Section -SR 37," A Report Presented the Advisory Board, Joint Highway Research Project, Purdue University, September 21, 1955, (Unpublished).
4. Wood, L. E. and Goetz, W. H., "The Strength of Bituminous Mixtures and Their Behavior Under Repeated Loads," Proceedings, Highway Research Board Volume 35, pp 405-417, 1956.
5. Wood, L. E. and Goetz, W. H., "The Strength of Bituminous Mixtures and Their Behavior Under Repeated Loads, Part II," Presented to the 36th Annual Meeting, Highway Research Board, Washington, D. C., January, 1957 (To Be Published).
6. Goetz, W. H., McLaughlin, J. F., and Wood, L. E., "Load Deformation Characteristics of Bituminous Mixtures Under Various Conditions of Loading," Presented to the Annual Meeting, The Association of Asphalt Paving Technologists, Atlanta, Georgia, February, 1957, (To Be Published).