Numerical examination of aggregate shape effect on chloride electromigration in concrete using multi-component ionic transport models

Qing-feng Liu^{a*}, Long-yuan Li^b and Jian Yang^{a,c}

a-School of Naval Architecture, Ocean & Civil Engineering, Shanghai Jiao Tong University, Shanghai, China

b-School of Marine Science and Engineering, University of Plymouth, PL4 8AA, UK

c-School of Civil Engineering, University of Birmingham, B15 2TT, UK

Abstract

This paper presents a numerical study on the mechanism of chloride migration in concrete. Unlike most of existing work, this study utilises multi-component ionic transport models to reflect the influence of ionic interactions by coupling both mass conservation and Poisson's equations. A series of 2-D, 3-phase models with different shapes and volume fractions of aggregates are developed to simulate the chloride migration test. Through a comparatively overall numerical exploration which considers external voltage, ionic interactions, heterogeneous nature, ITZ and ionic binding, some important features about multi-species coupling and aggregate shape effect, which have not been properly reported from existing concrete models, are highlighted.

Keywords: numerical modelling; concrete; aggregate shape; chloride; migration; heterogeneous; multi-phase; multi-species; ionic interaction; binding

*) Corresponding author: Tel: 86-1391 6655 773 Email: liuqf@sjtu.edu.cn

1. Introduction

Nowadays, chloride-induced corrosion of reinforced concrete (RC) structures has becoming a worldwide problem. It affects a large number of public infrastructure and buildings, particularly those used in offshore or exposed in marine environment. In order to prevent reinforcing bar from corrosion, one has to know the mechanism about how chlorides penetrate in concrete and how individual components in concrete respond while chlorides enter the concrete.

To characterise the transport behaviour of ionic species in concrete, during last decades, great efforts have been made on the assessment of ionic transport by using traditional approaches, i.e. analytical models [1]-[8] and/or experimental techniques[9]-[18]. However, note that concrete is a heterogeneous material with complicated meso- and micro-structure organisations, e.g., coarse/fine aggregate, cement paste, capillary/gel pores and cracks. For analytical studies, the main shortcoming is that they could only focus on the transport of ions in a 1-D single-phase medium (i.e., the cement or mortar matrix), neglecting the impact of inner structures of concrete. Moreover, due to the high nonlinear level of the problem of multi-component ionic transport, almost all existing analytical models consider the transport of only a single-species, i.e. the chloride ions. For experimental studies, though they can provide wider and valuable data, it is still very difficult for them to reveal individual effects of different factors because of the interactions between different factors. Also, most of testing methods are expensive and time-consuming, especially for the high-performance concrete specimens.

As neither of abovementioned method is appropriate to tackle the influences of individual components on chloride transport in concrete, finite element numerical models, originally

developed for the stress analysis of concrete, have recently been applied to investigate the transport properties of concrete with multiple phases [19]-[32]. By using this type of multi-phase computational model, one can easily clarify and quantify the influence caused by different structure of concrete, i.e., inclusion aggregates, mortar/cement and interfacial transition zones (ITZs), which is unavailable in one-phase analytical models. However, most of above work assumed circular or spherical particles for aggregates during modelling and this gross simplification may cause inaccuracy in simulation results. More recently, researchers further established mesostructures of concrete with several aggregate shapes to explore the aggregate shape effect on chloride diffusion in concrete. For example, Zheng et al. [33] developed a 2-D, 3-phase lattice model to investigate the shape effect of elliptical aggregate on chloride diffusion in concrete. They concluded that when the chloride diffusivity in concrete decreases with the increase of aspect ratio of elliptical aggregate particles. Dehghanpoor Abyaneh et al. [34] presented a 3-phase FEA model in three dimension to investigate the shape effect of various spheroidal aggregates (i.e., spherical, tri-axial ellipsoidal, prolate spheroidal, oblate spheroidal), and found that the diffusivity significantly decreased when spherical aggregate particles were replaced by ellipsoidal aggregate particles, particularly for higher aggregate fractions and aspect ratios.

Above numerical studies considered a diffusion problem and employed the Fick's first law to govern the steady-state chloride penetration in cracked concrete. In view of the long duration of diffusion tests and the need of electrochemical rehabilitation, the action of externally applied electric field is prevalently involved in a bunch of numerical models of chloride transport in concrete [35]-[53]. These models extended the ionic diffusion to a more complicated migration dominated process, which follows the applications of the rapid chloride permeability/migration (RCP/RCM) test [13]-[18] and the electrochemical chloride removal/extraction (ECR/ECE) treatment [54]. However, the convection-dominated diffusion

equations caused due to the presence of external electric field can create some numerical difficulties both in meshing and computing due to the Peclet number issue [39][40][49]. Thus, in order to achieve convergent results, most of these studies only adopted the models of 1-D without aggregate phase or 2-D but only with circular aggregates for simplification.

The literature survey described above shows that the aggregate shape effect on the transport properties of mortar or concrete has not been investigated in existing numerical models which take the action of externally applied electric field into account. Literature also indicates that the models with consideration of interaction between multiple ionic species controlled by Poisson's equation, which represents the true electrochemistry law for determining electrostatic potential in the transport medium, can provide more accurate results than those with only single ionic species or those consider multi-species in the pore solution but use the assumption of electro-neutrality condition [36]-[40]. In this paper, a numerical study is presented for theoretically investigating the aggregate shape effect during multiple ionic electromigration in concrete. A series of 2-D, 3-phase models with different shapes and volume fractions of aggregates are developed to simulate the chloride migration (RCM) test. Considering existing studies on aggregate shape effect [33],[34] did not discuss or show the details of chloride penetration in concrete (which is the key information for calculating diffusivity via RCM test), this study also provides time and spatial distribution profiles of four involved ionic species (K^+ , Na^+ , Cl^- , OH^-) by solving both mass conservation and Poisson's equations. Through a comparatively overall numerical exploration including external voltage, ionic interactions, binding effect, ITZs, non-steady state process and aggregate shape factor, some important features which have not been properly reported from existing concrete transport models, are highlighted.

2. Theoretical background

Concrete pore solution is a multi-component electrolyte involving not only chloride ions but also other ions such as sodium, potassium, hydroxyl, sulphate, and calcium etc. For the cases of diffusion tests, the transport of ions in a saturated concrete is mainly driven by the concentration gradient of the species itself and can be described as Fick's first law, which is most utilised in the durability study of the cracked concrete [19]-[34]. When the electrostatic potential is involved such as in migration tests [13]-[18], the more significant driving force of ionic transport is the electrostatic potential gradient, in which case the flux of an ionic species can be expressed using the Nernst-Planck equation as follows,

$$\mathbf{J}_k = -D_k \nabla C_k - D_k C_k \frac{z_k F}{RT} \nabla \Phi \quad (1)$$

where $\mathbf{J}_k$ is the flux, C_k is the concentration, D_k is the diffusion coefficient (note that in the heterogeneous concrete model, D_k has to be defined separately in different phases), z_k is the charge number, $F = 9.648 \times 10^4 \text{ Cmol}^{-1}$ is the Faraday constant, $R = 8.314 \text{ J mol}^{-1} \text{ K}^{-1}$ is the ideal gas constant, $T = 298 \text{ K}$ is the absolute temperature, Φ is the electrostatic potential, and the subscript k represents the k -th ionic species. Assume that the concrete is saturated and there is no chemical reaction taking place between ionic species, the following mass conservation defined in unit volume of electrolyte solution for each individual ionic species can be obtained,

$$\frac{\partial C_k}{\partial t} = -\nabla \cdot \mathbf{J}_k \quad (2)$$

where t is the time. When applying the ionic transport equations from an electrolyte solution to a porous material, one has to consider the ionic binding at pore surface. Therefore, Eq. (2) need be modified as follows,

$$\frac{\partial C_k}{\partial t} + \frac{\partial S_k}{\partial t} = -\nabla \cdot \mathbf{J}_k \quad (3)$$

where S_k is the concentration of bound ions of species k . It is suggested that the relationship between the bound and free chloride concentrations is almost independent of its transport rate and may satisfies the linear, Langmuir, or Freundlich isotherm [55] depending on its concentration. Recent work [56] highlighted the significant role of binding effect during the ingress of chlorides in cracked concrete and it is suggested to utilise a simple linear isotherm to express the relationship between free and bound ions for enhancing numerical stability,

$$S_k = \lambda C_k \quad (4)$$

where λ is a dimensionless fitting constant. Note that for constant λ , the term $(1 + \lambda)$ can be absorbed into the time term and in this case the difference between the considerations of binding and non-binding does not affect the governing equation and is only reflected by a time factor.

Substituting Eqs. (1) and (4) into (3), it yields,

$$(1 + \lambda) \frac{\partial C_k}{\partial t} = \nabla(D_k \nabla C_k) + \nabla \left[\left(\frac{z_k D_k F}{RT} \right) C_k \nabla \Phi \right] \quad (5)$$

In most of numerical models considering multi-species transport in concrete [35],[41]-[49], the electrostatic potential is often determined by using the assumption of electro-neutrality condition. This implies that the spatial electrostatic potential is purely caused by the externally applied electric field and the charge balance of species occurs everywhere in the solution domain. In this case the concentration of each ionic species can be calculated independently using Eq. (5) by employing $\nabla^2 \Phi = 0$. Apparently, this assumption makes the multi-species transport behave as a single-component model, which does not reflect the

actual interaction between different ionic species [51]. The essence of this issue is that, in fact, the electrostatic potential is generated by not only the externally applied electric field but also the significant internal charge imbalance between different ionic species. This charge imbalance within the concrete medium attributes to two reasons. The first one is that under the action of external electric field the cations and anions have opposite-direction movement. The second one is that the different ionic species usually have different diffusion coefficients and thus travel in different speeds in this multi-component system. In general, the generated charge imbalance creates an internal electrostatic potential which can affect the transport of all ionic species in the concrete throughout the time and space. This electrostatic potential increases with the externally applied electric field and the difference of diffusivities between ionic species. In order to accurately describe the internal charge imbalance between different species and also achieve the true multi-species coupling, recent work [36]-[40] suggested that one should use the following Poisson's equation to govern the electrostatic potential in the transport medium,

$$\nabla^2 \Phi = -\frac{F}{\varepsilon_0 \varepsilon_r} \sum_{k=1}^N z_k C_k \quad (6)$$

where $\varepsilon_0 = 8.854 \times 10^{-12} \text{ CV}^{-1}\text{m}^{-1}$ is the permittivity of a vacuum, $\varepsilon_r = 78.3$ is the relative permittivity of water at temperature of 298 K, and N is the total number of ionic species involved in the solution. For numerical modelling, the use of Poisson's equation creates two difficulties. One is the coupling of Eq. (5) between different ionic species, since Φ is now dependent on not only the boundary conditions defined by the externally applied electric field, but also the concentrations of all ionic species involved in the medium. The other is the nonlinearity and numerical difficulty which involves calculations of large and small numbers that need be handled carefully [39],[40]. Nevertheless, Eqs. (5) and (6) can be used to determine the electrostatic potential, Φ , and the concentrations of individual ionic species, C_k

($k=1,2,\dots,N$), at any time and any point in the solution domain, provided that the initial and boundary conditions are properly defined.

3. Modelling

The concrete modelled in this study is treated as a heterogeneous composite structure with three phases consisting of mortar matrix, coarse aggregates and ITZs. Most of existing multi-phase models [19]-[31] including previous work as well [[40],[48]-[52], assumed circular or spherical aggregates for simplification. Fig.1 shows one of the 2-D concrete numerical models with the size of 50×50 mm. The volume fraction of aggregates is $V_{\text{agg}} = 0.5$. In the figure all circular areas represent the impermeable aggregates with the radii ranging from 1.5 mm to 10 mm. Outside each aggregate, there is an aureole ITZ shell of tiny scale wrapping the aggregate. Outside the ITZs, the remaining part of the concrete model represents the mortar matrix. The location of the aggregates was randomly generated using a MATLAB program. It should be mentioned that, the shape of aggregates may not be perfectly circular in reality. Thus, in order to further investigate the effect caused by aggregate shapes and volume fractions, a set of 2-D concrete numerical models with various shapes and volume fractions of coarse aggregates were developed herein. Fig.2 shows the meshed models with the same aggregates volume fraction of $V_{\text{agg}} = 0.5$ but different aggregates shapes: ellipse, triangle, rectangle, and mixed shapes. As the aggregates are assumed to be impermeable, only the mortar phase is meshed. It is also noticeable from Fig.2 that, the distributions of ellipse, triangle, rectangle aggregates are almost uniform whereas only that of mixed shaped aggregates is less uniform. A careful examination of the geometry including mixed particles shows that, the smaller sized particles gather more in the region near the cathode (from $x=0$ to $x=0.025$), whereas the larger ones gather more in the region near the anode (from $x=0.025$

to $x=0.05$). This setting is deliberately arranged for legible exploration of the influence of tortuosity, which will be explained later in discussions.

The model described above is used to simulate the RCM test of concrete, in which the 50 mm x 50 mm plain concrete specimen is located between two compartments, one of which has a 0.52 mole/l NaCl solution, the other of which has a 0.30 mole/l NaOH solution. An external potential difference of 24 V is applied between two electrodes inserted into the two compartment solutions. The ionic species to be analysed in the simulations include potassium, sodium, chloride and hydroxyl. Note that other ionic species (such as calcium and sulphate) may also exist in the concrete. However, owing to their low concentrations they are not considered in the present simulations. The ionic transport parameters employed for different phases are listed in Table 1. Fig. 3 graphically displays the simulated test. Note that since the volume of either compartment is much greater than that of the specimen, it is reasonable to assume that the concentrations of each ionic species in the two compartments remain constants during the migration test. Table 2 shows the initial and boundary conditions employed in the present study.

4. Results and Discussions

For given initial and boundary conditions, the ionic transport in the simulated concrete specimens can be numerically calculated by solving the mass conservation equation and Poisson equation. As particular interest is of the penetration of chloride ions, here, only the chloride distribution profiles are displayed in the form of the 3-D plot, which are shown in Figs. 4-8. Generally speaking, with the same aggregates volume fraction, the evolutions of ionic transports in the models filled by ellipse, triangle, rectangle, and mixed shaped aggregates closely resemble that in the circular shaped model. The negatively charged

chlorides steadily move from the cathode towards the anode by electro-migration process, which takes place mainly along the x-axis direction. It also can be seen from the figures that, the aggregates split the migration wave fronts into a number of pieces which makes the wave front act like a 'waterfall'. Generally, the pieces of 'waterfall' move at a synchronous velocity throughout the most 3-D figures. However, in the triangle shaped aggregate model (Fig. 6), it is noticeable that the speeds of the 'waterfall' pieces are not parallel and ordered. This phenomenon can be explained by the effect of tortuosity. The sharp angle of triangle shape will markedly increasing the length of the flow paths as well as generates many local corner pockets in the electrolyte solution to decrease the transport of ions in corresponding areas.

For a more quantitative study, Figs. 9-12 give comparisons of concentration profiles of four ionic species between five different shapes when they have the same volume fraction of aggregates. It is clearly shown that, there is only a tiny difference in the migration velocities between the models with the shapes of circular, ellipse and rectangle, which implies a similar tortuosity between the models with these shapes of inclusion. In contrast, from the overall points of view, the triangle shaped aggregates bring a slower velocity than other shaped aggregates due to its largest tortuosity.

More interesting features are found in the mixed shaped aggregates. As it was mentioned above that the distribution of the different sized aggregates are deliberately arranged to be less uniform (the smaller ones more gathers in the left side of the concrete specimen and the larger ones do the opposite), the tortuosity of the model including mixed shaped aggregates is correspondingly less uniform (larger tortuosity in region near the cathode and smaller tortuosity in region near the anode). As a consequence, when the migration waves of the negatively charged ions (both chloride and hydroxide) of the mixed shaped aggregates travel

from the section of $x=0$ to the section of $x=0.025$, its speed is slower than the others, even including the triangle ones; when they travel from the section of $x=0.025$ to the section of $x=0.05$, the migration waves of the mixed shaped aggregates speed up, overtaking the triangle one and finally almost equalling the evolution of other three shaped aggregates at the region near the anode. This procedure exactly reverses when it happens to the positively charged ions (both potassium and sodium). The phenomenon described above evidently depicts how the tortuosity caused by the aggregate phase affects the ionic transport in concrete.

The above findings seem to indicate that, under the condition of identical volume fraction and similar tortuosity, the shape of aggregate has little impact on the penetrations of ions. To further prove this opinion, more examples are provided here of different shapes with different volume fractions. Figs. 13 and 14 respectively show the comparisons of different shapes under the aggregate volume fractions of $V_{agg} = 0.4$ and 0.3 . As it was expected, both figures again show that the migration velocities of chlorides are approximately a constant between various shapes, except for the triangle aggregates which has significantly larger tortuosity. Note that the aggregates of mixed shapes in this example are randomly distributed. Therefore, the special behaviour which occurs in Figs. 9-12 disappears in Figs. 13 and 14, in terms of the special results of triangle shaped aggregates. Note that triangle shaped aggregates are the extreme case which is very rare in reality. Therefore, it can be concluded that the influence of particle shapes on the permeability of concrete is not very significant.

In order to examine the influence of the volume fraction of aggregates on the ionic transport, particularly that of chloride ions, Fig. 15 shows the concentration distribution profiles of chloride ions at four different times for three different aggregate volume fractions. It can be seen from the figure that, the influence caused by various volume fractions is much more remarkable than that caused by various shapes. Specifically, the smaller the aggregate volume

fraction, the quicker the chloride ions can travel. The reason for this is still likely due to the effect of tortuosity, as the higher the aggregate volume fraction, the larger the tortuosity; therefore, the slower the ionic transport.

5. Conclusions

This paper has presented a numerical investigation on the transport properties of concrete based on a multi-phase, multi-component transport model. The model has been used to simulate RCM test as well as to examine the aggregate shape effect when consider the electrostatic coupling between ionic species. From the present study the following conclusions can be drawn.

- 1) The multi-species coupling has important influence on the electrostatic potential predicted in the multi-phase model. It significantly affects the migration speeds of ionic species. The influences on ionic species with different charges are considerably different.
- 2) Under the condition of identical volume fraction and similar tortuosity, the influence of particle shapes on the permeability of concrete is not very significant, except for that the triangle shaped aggregates bring a smaller diffusivity of ions than other shaped aggregates due to its largest tortuosity.
- 3) Relatively, the influence of volume fraction is much more significant than that of aggregate morphology, due to the more notable influence on tortuosity.
- 4) The inclusion of aggregates in the model can provide a more accurate influence of tortuosity on both the diffusion and migration of ions.

References

- [1] A. Atkinson, A. K. Nickerson, The diffusion of ions through water-saturated cement, *J. Mater. Sci.* 19 (1984) 3068–3078.
- [2] Hobbs DW. Aggregate influence on chloride ion diffusion into concrete. *Cement and Concrete Research* 1999; 29: 1995–1998.
- [3] E. J. Garboczi, Permeability, diffusivity, and microstructural parameters: a critical review, *Cement Concrete Res.* 20 (4) (1990) 591-601.
- [4] J. V. Brakel, P. M. Heertjes, Analysis of diffusion in macroporous media in terms of porosity, a tortuosity and a constrictivity factor, *Int. J. Heat Mass Tran.* 17 (9) (1974) 1093-1103.
- [5] Garboczi EJ, Bentz DP. Analytical formulas for interfacial transition zone properties. *Advanced Cement Based Materials* 1997; 6(3-4): 99-108.
- [6] K. Xu, JF. Daian, D. Quenard, Multiscale structures to describe porous media part II: transport properties and application to test materials, *Transport Porous Med.* 26 (3) (1997) 319-338.
- [7] Xi Y, Bazant ZP. Modeling chloride penetration in saturated concrete. *Journal of Materials in Civil Engineering* 1999; 58–65.
- [8] Byung HO, Seung YJ. Prediction of diffusivity of concrete based on simple analytical equations. *Cement and Concrete Research* 2004; 34(3): 463-480.
- [9] AASHTO T 259, Standard Method of Test for Resistance of Concrete to Chloride Ion Penetration, American Association of States Highway and Transportation Officials, Washington, 2003.
- [10] ASTM C1543, Standard Test Method for Determining the Penetration of Chloride Ion into Concrete by Ponding, ASTM International, West Conshohocken, PA, 2010.
- [11] NT Build 443, Concrete, Hardened: Accelerated Chloride Penetration, Nordtest Method, 1995. Helsingfors.
- [12] ASTM C1556, Standard Test Method for Determining the Apparent Chloride Diffusion Coefficient of Cementitious Mixtures by Bulk Diffusion, ASTM International, West Conshohocken, PA, 2011.
- [13] D. Whiting, Rapid measurement of the chloride permeability of concrete, *Public Roads* 45 (3) (1981) 101–112.
- [14] AASHTO T 277, Standard Method of Test for Rapid Determination of the Chloride Permeability of Concrete, American Association of States Highway and Transportation Officials, Washington, 1983.
- [15] ASTM C 1202, Standard Test Method for Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration, American Society for Testing and Materials, Philadelphia, 1994.
- [16] L. Tang, L.O. Nilsson, Rapid determination of the chloride diffusivity in concrete by applying an electric field, *ACI Mater. J.* 89 (1) (1993) 49–53.
- [17] NT-Build 492. Nordtest Method: Concrete, Mortar and Cement-Based Repair Materials: Chloride Migration Coefficient from Non-Steady-State Migration Experiments. (1999).
- [18] AASHTO TP 64-03, Standard Method of Test for Prediction of Chloride Penetration in Hydraulic Cement Concrete by the Rapid Migration Procedure, American Association of State Highway and Transportation Officials, Washington, 2003.
- [19] Bentz DP, Garboczi EJ. Percolation of phases in a three-dimensional cement paste microstructural model. *Cement and Concrete Research* 1991; 21(2-3): 325-344.
- [20] Bourdette B, Ringot E, Ollivier JP. Modeling of the transition zone porosity. *Cement and Concrete Research* 1995; 25(4): 741-751.

- [21] Garboczi EJ, Bentz DP. Multiscale analytical/numerical theory of the diffusivity of concrete. *Advanced Cement Based Materials* 1998; 8(2): 77-88.
- [22] Yang CC, Weng SH. A three-phase model for predicting the effective chloride migration coefficient of ITZ in cement-based materials. *Magazine of Concrete Research* 2013; 65(3): 193-201.
- [23] Caré S. Influence of aggregates on chloride diffusion coefficient into mortar. *Cement and Concrete Research* 2003; 33(7): 1021–1028.
- [24] Caré S, Hervé E. Application of a n-phase model to the diffusion coefficient of chloride in mortar. *Transport Porous Media* 2004; 56(2): 119–135.
- [25] Zeng YW. Modeling of chloride diffusion in hetero-structured concretes by finite element method. *Cement & Concrete Composites*, 2007, 29: 559–565.
- [26] Zheng JJ, Wong HS, Buenfeld NR. Assessing the influence of ITZ on the steady-state chloride diffusivity of concrete using a numerical model. *Cement and Concrete Research*, 2009, 39: 805–813.
- [27] Sun G, Zhang Y, Sun W, Liu Z, Wang C. Multi-scale prediction of the effective chloride diffusion coefficient of concrete. *Construction and Building Materials*, 2011, 25: 3820–3831.
- [28] Xiao J, Ying J, Shen L. FEM simulation of chloride diffusion in modeled recycled aggregate concrete. *Construction and Building Materials*, 2012, 29: 12–23.
- [29] Jiang JY, Sun GW, Wang CH. Numerical calculation on the porosity distribution and diffusion coefficient of interfacial transition zone in cement-based composite materials. *Construction and Building Materials*, 2013, 39: 134–138.
- [30] Ying JW, Xiao JZ, Shen LM, Bradford MA. Five-phase composite sphere model for chloride diffusivity prediction of recycled aggregate concrete. *Magazine of Concrete Research* 2013; 65(9): 573-588.
- [31] Yang CC, Weng SH. A three-phase model for predicting the effective chloride migration coefficient of ITZ in cement-based materials. *Magazine of Concrete Research* 2013; 65(3): 193-201.
- [32] Li LY, Xia J, Lin SS. A multi-phase model for predicting the effective diffusion coefficient of chlorides in concrete. *Construction and Building Materials*, 2012, 26 (1): 295–301.
- [33] Zheng JJ, Zhou XZ, Wu YW, Jin XY. A numerical method for the chloride diffusivity in concrete with aggregate shape effect. *Construction and Building Materials*, 2012, 31: 151–156.
- [34] Abyaneh SD, Wong HS, Buenfeld NR. Modelling the diffusivity of mortar and concrete using a three-dimensional mesostructure with several aggregate shapes. *Computational Materials Science*, 2013, 78: 63–73.
- [35] G.A. Narsillo, R. Li, P. Pivonka, D.W. Smith. Comparative study of methods used to estimate ionic diffusion coefficients using migration tests. *Cement and Concrete Research* 37 (2007) 1152-1163.
- [36] B. Johannesson, K. Yamada, L.O. Nilsson, Y. Hosokawa. Multi-species ionic diffusion in concrete with account to interaction between ions in the pore solution and the cement hydrates. *Materials and Structures* 40 (2007) 651-665.
- [37] E. Samson, J. Marchand. Modeling the transport of ions in unsaturated cement-based materials. *Computers & Structures* 85 (2007) 1740-1756.
- [38] K. Krabbenhoft, J. Krabbenhoft. Application of the poisson-nernst-planck equations to the migration test. *Cement and Concrete Research* 38 (2008) 77-88.
- [39] J. Xia, L.Y. Li. Numerical simulation of ionic transport in cement paste under the action of externally applied electric field. *Construction and Building Materials* 39 (2013) 51-59.
- [40] Q.F. Liu, L.Y. Li, D. Easterbrook, J. Yang. Multi-phase modelling of ionic transport in

- concrete when subjected to an externally applied electric field. *Engineering Structures* 42 (2012) 201–213.
- [41] M.M. Jensen, B. Johannesson, M.R. Geiker. Framework for reactive mass transport: Phase change modeling of concrete by a coupled mass transport and chemical equilibrium model. *Computational Materials Science* 92 (2014) 213–223.
 - [42] L.Y. Li, C.L. Page. Modelling and simulation of chloride extraction from concrete by using electrochemical method. *Computational Materials Science* 9 (1998) 303–308.
 - [43] F. Frizon, S. Lorente, J.P. Ollivier, P. Thouvenot. Transport model for the nuclear decontamination of cementitious materials. *Computational Materials Science* 27 (2003) 507–516.
 - [44] O. Truc, J.P. Ollivier, L.O. Nilsson. Numerical simulation of multi-species transport through saturated concrete during a migration test--MSDIFF code. *Cement and Concrete Research* 30 (2000) 1581–1592.
 - [45] Y. Wang, L.Y. Li, C.L. Page. A two-dimensional model of electrochemical chloride removal from concrete. *Computational Materials Science* 20 (2001) 196–212.
 - [46] A. Toumi, R. Francois, O. Alvarado. Experimental and numerical study of electrochemical chloride removal from brick and concrete specimens. *Cement and Concrete Research* 37 (2007) 54–62.
 - [47] Y. Liu, X. Shi. Ionic transport in cementitious materials under an externally applied electric field: Finite element modeling. *Construction and Building Materials* 27 (2012) 450–460.
 - [48] Q.F. Liu, J. Xia, D. Easterbrook, J. Yang, L.Y. Li. Three-phase modeling of electrochemical chloride removal from corroded steel-reinforced concrete. *Construction and Building Materials* 70 (2014) 410–427.
 - [49] Šavija B, Luković M, Schlangen E. Lattice modeling of rapid chloride migration in concrete[J]. *Cement and Concrete Research*, 2014, 61–62: 49–63.
 - [50] Liu QF, Easterbrook D, Yang J, Li LY. A three-phase, multi-component ionic transport model for simulation of chloride penetration in concrete. *Engineering Structures*, 2015, 86: 122–133.
 - [51] Liu QF, Yang J, Xia J, Easterbrook D, Li LY, Lu XY. A numerical study on chloride migration in cracked concrete using multi-component ionic transport models. *Computational Materials Science*, 2015, 99: 396–416.
 - [52] Feng GL, Li LY, Kim B, Liu QF. Multiphase modelling of ionic transport in cementitious materials with surface charges. *Computational Materials Science* 111 (2016) 339–349.
 - [53] Li LY, Easterbrook D, Xia J, Jin WL. Numerical simulation of chloride penetration in concrete in rapid chloride migration tests. *Cement & Concrete Composites* 63 (2015) 113–121.
 - [54] D.R. Lankard, J.E. Slatter, W.A. Holden, D.E. Niess. Neutralization of chloride in concrete, FHWA Report No. FHWA-RD-76-6, Battelle Columbus Laboratories, (1975).
 - [55] L. Tang, L.O. Nilsson. Chloride binding capacity and binding isotherms of OPC pastes and mortars. *Cement and Concrete Research* 23 (1993) 247–253.
 - [56] D.P. Bentz, E.J. Garboczi, Y. Lu, N. Martys, A.R. Sakulich, W.J. Weiss. Modeling of the influence of transverse cracking on chloride penetration into concrete. *Cement and Concrete Composites* 38 (2013) 65–74.

Table 1. Ionic transport properties in different phases

Field variables	Potassium (mole/m ³)	Sodium (mole/m ³)	Chloride (mole/m ³)	Hydroxide (mole/m ³)
Charge number	1	1	-1	-1
Diffusion coefficient in aggregates, D_A	0	0	0	0
Diffusion coefficient in bulk mortar, $D_B, \times 10^{-10} \text{ m}^2/\text{s}$	3.914	2.668	4.064	10.52
Diffusion coefficient in ITZs, $D_I \times 10^{-9} \text{ m}^2/\text{s}$	1.174	0.800	1.219	3.156

Table 2. Initial and boundary conditions of individual species

Field variables		Potassium	Sodium	Chloride	Hydroxide	Electrostatic potential
Concentration boundary conditions, mole/m ³	x = 0	0	520	520	0	0
	x = L	0	300	0	300	24 V
Flux boundary conditions	y = 0	J = 0	J = 0	J = 0	J = 0	$\partial\Phi/\partial y=0$
	y = L	J = 0	J = 0	J = 0	J = 0	$\partial\Phi/\partial y=0$
Initial conditions, mole/m ³	t = 0	200	100	0	300	0

Figure 1. Geometry sample of 2D multi-phase concrete model: section of concrete, $V_{\text{agg}} = 0.5$.

Figure 2. Finite element mesh of geometries with various shaped aggregates, $V_{\text{agg}} = 0.5$.

Figure 3. Schematic representation of 2-D plain concrete specimen in a RCM test..

Figure 4. Concentration distribution profiles of chloride ions (for aggregates with a circular shape).

Figure 5. Concentration distribution profiles of chloride ions (for aggregates with an ellipse shape).

Figure 6. Concentration distribution profiles of chloride ions (for aggregates with a triangle shape).

Figure 7. Concentration distribution profiles of chloride ions (for aggregates with a rectangle shape).

Figure 8. Concentration distribution profiles of chloride ions (for aggregates with mixed shapes).

Figure 9. Comparisons of potassium concentration profiles between different aggregate shapes, $(1-\phi) = 0.5$.

Figure 10. Comparisons of sodium concentration profiles between different aggregate shapes, $(1-\phi) = 0.5$

Figure 11. Comparisons of chloride concentration profiles between different aggregate shapes, $(1-\phi) = 0.5$.

Figure 12. Comparisons of hydroxide concentration profiles between different aggregate shapes, $(1-\phi) = 0.5$.

Figure 13. Comparisons of chloride concentration profiles between different aggregate shapes, $(1-\phi) = 0.4$.

Figure 14. Comparisons of chloride concentration profiles between different aggregate shapes, $(1-\phi) = 0.3$.

Figure 15. Comparisons of chloride concentration profiles between different volume fractions (circular aggregates)